

RTV Silicones



ALL MG PRODUCTS ▾

Jump to Product Number



- [Accessories](#)
- [Adhesives](#)
- [Brushes](#)
- [Cleaners / Degreasers](#)
- [Contact Cleaners](#)
- [Desoldering Braid](#)
- [Dusters & Circuit Coolers](#)
- [EMI / RFI Shielding](#)
- [Epoxyes](#)
- [Flux and Flux Remover](#)
- [Glass & Screen Cleaners](#)
- [Isopropyl Alcohol](#)
- [Lead Free Solder](#)
- [Lubricants](#)
- [Potting & Encapsulating](#)
- [Protective Coatings](#)
- [Pens](#)
- [Prototyping Materials](#)
- [RTV Silicones](#)
- [Soldering/desoldering](#)
- [Specialized Cleaners](#)
- [Swabs](#)
- [Thermal Management](#)
- [Thermally Conductive Adhesives](#)
- [Wipes](#)

# RTV Silicones by MOMENTIVE 1-Part Adhesive Sealant RTV167



[▶ BUY NOW](#)

- Primary Characteristics**
- ▶ Light Gray Paste
  - ▶ **High strength electronics**
  - ▶ Non-corrosive
  - ▶ **Alkoxy neutral cure**
  - ▶ MIL-A-46146, group 1, type 1
  - ▶ UL HB recognition
  - ▶ UL File No. [E36952](#)

Excellent in areas that require an extra strength sealing and bonding. Non-corrosive to electronic metals, including copper and brass. Can be applied to vertical or overhead surfaces. Retains elastomeric properties for long periods at temperatures from -60°C to 205°C (75°F to 400°F) and for short periods up to 250°C (500°F). Excellent electrical insulating properties. This product meets Military spec. MIL-A-46146 and is UL HB recognized.

## Available Sizes

Catalog Number	Sizes Available	Description	Case Qty
RTV167-85ML	85 mL (2.8 oz)	Tube	12
RTV167-300ML	<b>▶ SPECIAL ORDER</b> 300mL (10 oz)	Cartridge	24

## Specifications

Use	Adhesive Sealant
Special Feature	High tensile strength
Standards	MIL-A-46146, group 1, type 1 UL File no. E-36952
Cross Reference	RTV167
<b>Uncured Properties</b>	
Consistency	Paste
Color	Grey
Specific Gravity	1.12
Tack Free Time	4 hours
Cure through time	48 hours
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
<b>Cured Properties - MECHANICAL</b>	
<a href="#">Hardness</a>	37 (Shore A)
Tensile Strength	5.49 MPa (800 psi)
Elongation	600%
Peel Strength	10 kg/cm 80 lb/in
<b>Cured Properties - ELECTRICAL</b>	
Volume Resistivity	3 x 10 <sup>15</sup> ohm · cm
Dielectric Strength	19.7 kV/mm 500 V/mil
Dielectric Constant	2.8 @ 60 Hz
<b>Cured Properties - THERMAL</b>	

Technical Support  
for RTV Silicones

1-800-255-8886

M.G. Chemicals Disclaimer  
for RTV Silicones >

[Locate Distributor >](#)

## Quick Links

- ▶ [MSDS](#)
- ▶ [Specifications](#)
- ▶ [Available Sizes](#)

## Related products:

- [RTV160 White](#)
- [RTV162 White](#)
- [TSE397C Clear](#)
- [TSE399C Clear](#)

## Resources

- ▶ [Selection Guide >](#)
- ▶ [One Part Chart](#)
- ▶ [Two Part Chart](#)

## Find by Application

- [General Purpose >](#)
- [Aerospace >](#)
- [Marine >](#)
- [High Performance Assembly >](#)
- [Electronics >](#)
- [Thermal Conductivity >](#)
- [High Temperature >](#)
- [Low Temperature >](#)



Thermal Conductivity	0.21 W/m · °K
Brittle Point	-60°C (-75°F)
Thermal Expansion	27 x 10 <sup>-5</sup> (°C) <sup>-1</sup>
Other	
<a href="#">Viscosity</a> (@ 25°C)	180 g/min

[Return to top](#) ^